

Fine Powder of Low Sodium α -Calcined Alumina (Rotary Kiln)

Main Uses of The Product

- Advanced refractory materials
- High-end ceramic products
- Electronic ceramics
- Functional ceramics

Product Characteristic Index

Product Model	Chemical Composition (%)				Loss on Ignition (%) (\leq)	325 Sieve Oversize (%) (\leq)	Median particle size(μ m)
	Al2O3 (\geq)	SiO2 (\leq)	Fe2O3 (\leq)	Na2O (\leq)			
A-CG-200MS	99.3	0.15	0.04	0.20	0.25	3	1-3
A-CG-300MS	99.3	0.15	0.04	0.20	0.25	3	3-6
A-CG-300LS	99.3	0.15	0.04	0.10	0.25	3	3-6

Note: The particle size can be adjusted according to customer requirements