

Ultra-low Sodium Calcined α Alumina (Fine Powder)

Main Uses of The Product

- Structural ceramics
- Functional ceramics such as electronic ceramics
- High-end refractory materials
- Advanced polishing and grinding materials
- Lithium battery diaphragm coating, etc.

Product Characteristic Index

Product Model	Chemical Composition (%)				Loss on Ignition (%) (\leq)	325 Sieve Oversize (%) (\leq)	Median particle size(μ m)
	Al2O3 (\geq)	SiO2 (\leq)	Fe2O3 (\leq)	Na2O (\leq)			
ACG-100	99.7	0.1	0.02	0.05	0.25	3	\leq 1
ACM-200	99.7	0.1	0.02	0.05	0.25	3	1-2
ACG-200	99.7	0.1	0.02	0.05	0.25	3	2-5
ACG-400	99.7	0.1	0.02	0.05	0.25	3	3-6